



938 Valen-t (exp.)

Uso recomendado/recommended end-use:
Prenda POLAR / POLAR garment

Composición/composition:

52% PES
24% Acrílica modificada tipo-F/
Modified acrylic fibre type-f
16% Viscosa/Viscose
7% P-Aramida/P-Aramide
1% Antiestático/Antistatic



LIGAMENTO / LIGAMENT	Rizo Polar / Polar Fleece	
PESO / WEIGHT (gr/m ²)	380 ± 5%	UNE 40339-2002
ANCHO / WIDTH (cm)	170 ± 1	
PILLING MARTINDALE (5.000 cycles)	4-5	EN 12945-2
ENCOGIMIENTO AL LAVADO / WASHING SHRINKAGE	5%	UNE-EN ISO 6330

PRETRATAMIENTO / PRE-TREATMENT	5 washes	50 washes	
INFLAMABILIDAD / INFLAMMABILITY	A1	A1	EN 15025 (EN 11612)
CALOR CONVECTIVO / CONVECTIVE HEAT	B1	B1	ISO 9151
CALOR RADIANTE/ RADIANT HEAT	C2	C2	ISO 6942
CALOR POR CONTACTO / CONTACT HEAT	F1	F2	EN ISO 12127-2
ANTIESTÁTICO / ANTISTATIC	Pass	Pass	EN 1149/5
ARCO ELÉCTRICO / ELECTRIC ARC	ATPV: 10,4 cal/cm ² 4kA Class 1	Not tested 4kA Class 1	ASTM F1959 EN 61482-1-2
ALTA VISIBILIDAD / HIGH VISIBILITY	Pass	Not tested	EN 20471

Condiciones de lavado EN 6330/ / Washing instructions EN 6330/



*Evitar utilizar suavizantes / Avoid using softeners