



## 812 Xispal RS

Uso recomendado/recommended end-use:  
FORRO INTERIOR / INNER LINING

Composición/composition:  
50% Algodón / Cotton  
39% Acrílica modificada Tipo-F/  
Modified acrylic fibre type-F  
10% Viscosa / Viscos  
1% Antiestático/Antistatic



LIGAMENTO / LIGAMENT	Plana / Tafetan	
PESO / WEIGHT (gr/m <sup>2</sup> )	120 ± 5%	UNE 40339-2002
ANCHO / WIDTH (cm)	150 ± 1	
RESISTENCIA A LA TRACCIÓN TENSILE STRENGTH (rg W x F)	65 ± 5% 20 ± 5%	UNE-EN ISO 13934-1
PILLING MARTINDALE (5.000 cycles)	5	EN 12945-2
PRETRATAMIENTO / PRE-TREATMENT	5 washes	
ENCOGIMIENTO AL LAVADO / WASHING SHRINKAGE	3%	UNE-EN ISO 6330
INFLAMABILIDAD / INFLAMMABILITY	A1	EN 15025 ( EN 11612)
ANTIESTÁTICO / ANTISTATIC	Pass	EN 1149/3

Condiciones de lavado EN 6330 (60°C) / Washing instructions EN 6330 (60°C)

