



820 R1 Xispal RS

Uso recomendado/recommended end-use:
CAZADORA O CAMISA Y PANTALÓN /
JACKET OR SHIRT & PANTS

Composición/composition:
42% Acrílica modificada Tipo-F/
Modified acrylic fibre type-f
25% Algodón / Cotton
22% Poliamida / Polyamide
10% Viscosa / Viscose
1% Antistatic



LIGAMENTO / LIGAMENT	Sarga / Twill	
PESO / WEIGHT (gr/m ²)	200 ± 5%	UNE 40339-2002
ANCHO / WIDTH (cm)	160 ± 1	
PILLING MARTINDALE (5.000 cycles)	5	EN 12945-2
ENCOGIMIENTO AL LAVADO / WASHING SHRINKAGE	3%	UNE-EN ISO 15797

PRETRATAMIENTO / PRE-TREATMENT	5 washes	50 washes	
RESISTENCIA A LA TRACCIÓN TENSILE STRENGTH (kg W x F)	130 ± 5% 53 ± 5%	90 ± 5% 60 ± 5%	UNE-EN 13934-1
INFLAMABILIDAD / INFLAMMABILITY	A1	A1	EN 15025 (EN 11612)
CALOR CONVECTIVO / CONVECTIVE HEAT	B1	B1	ISO 9151
CALOR RADIANTE/ RADIANT HEAT	C1	C1	ISO 6942
CALOR POR CONTACTO / CONTACT HEAT	F1	F1	EN ISO 12127-2
ARCO ELÉCTRICO / ELECTRIC ARC	4kA Class 1 ATPV: 9.2 cal/cm ²	4kA Class 1 Not tested	EN 61482-1-2 EN 61482-1-1 (NFPA 70 E)
ANTIESTÁTICO / ANTISTATIC	Pass	Pass	EN 1149-3-5
ANTIÁCIDO / ANTIACID	Pass	Not tested	EN 13034
ALTA VISIBILIDAD / HIGH VISIBILITY	Pass	Not tested	EN 20471

Condiciones de lavado EN 15797 / Washing instructions EN 15797:

