

847 R1 Softshell Xispal RS

Uso recomendado/recommended end-use:
PRENDAS IMPERMEABLES / RAINWEAR

Composición/composition:
36% Algodón / Cotton
32% Acrílica modificada Tipo-F/
Modified acrylic fibre type-f
16% Viscosa / Viscose
8% PU
7% Poliamida / Polyamide
1% Antiestático/Antistatic



LIGAMENTO / LIGAMENT	Plana + Interlock	
PESO / WEIGHT (gr/m ²)	470 ± 5%	UNE 40339-2002
ANCHO / WIDTH (cm)	150 ± 1	
PILLING MARTINDALE (5.000 cycles)	4	EN 12945-2

PRETRATAMIENTO / PRE-TREATMENT	5 washes	50 washes	
ENCOGIMIENTO AL LAVADO / WASHING SHRINKAGE	5%	Not tested	UNE-EN ISO 15797
INFLAMABILIDAD / INFLAMMABILITY	A1-A2	A1-A2	EN 15025 (EN 11612)
CALOR CONVECTIVO / CONVECTIVE HEAT	B1	B1	ISO 9151
CALOR RADIANTE/ RADIANT HEAT	C2	C2	ISO 6942
CALOR POR CONTACTO / CONTACT HEAT	F2	F2	EN ISO 12127-2
ANTIESTÁTICO / ANTISTATIC	Pass	Pass	EN 1149/3/5
ANTIÁCIDO / ANTIACID (opcional/optional)*	Pass	No tested	EN 13034
ARCO ELÉCTRICO / ELECTRIC ARC	7kA - class 2	No tested	EN 61482-1-2
TRANSPIRABILIDAD / PERSPIRATION	Class 1	No tested	EN 343
IMPERMEABILIDAD / WATERPROOF	Class 4	No tested	EN 343

*Prendas antiácidas: polimerizar 2 minutos a 160°C o aditivar con acabado fluorocarbonado tras cada ciclo de lavado / Antacid garments: polymerize 2 minutes at 160°C or add fluorocarbon finish after each washing cycle

Condiciones de lavado EN 6330 (60°C) / Washing instructions EN 6330 (60°C)

