

# 825 Xispal RS

Rev. 5

Uso recomendado /  
Recommended end-use:  
CAZADORA Y PANTALÓN /  
JACKET & PANTS

Composición / Composition:

**50% Algodón / Cotton**

**39% Acrílica modificada tipo-F / Modified acrylic fibre type-F**

**10% Viscosa / Viscose**

**1% Antiestático / Antistatic**



825 Xispal RS

LIGAMENTO / LIGAMENT		Sarga / Twill		
PESO / WEIGHT (gr/m <sup>2</sup> )		250 ± 5%		UNE 40339
ANCHO / WIDTH (cm)		160 ± 1		
PILLING MARTINDALE (5.000 cycles)		5		EN 12945-2
ENCOGIMIENTO AL LAVADO / WASHING SHRINKAGE		3%		UNE-EN ISO 15797
PRETRATAMIENTO / PRE-TREATMENT		5 washes	50 washes	
RESISTENCIA A LA TRACCIÓN (N U x T) TENSILE STRENGTH (N W x F)		900 ± 5% 450 ± 5%	800 ± 5% 500 ± 5%	UNE-EN 13934-1
INFLAMABILIDAD / INFLAMMABILITY		A1-A2	A1-A2	EN 15025 (EN 11612)
CALOR CONVECTIVO / CONVECTIVE HEAT		BI	BI	ISO 9151
CALOR RADIANTE / RADIANT HEAT		CI	CI	ISO 6942
RESIST. A GRAN SALPICADURA. BIG SPLASH RESIST.	ALUMINIUM (780°C)	DI	DI	ISO 9185
	IRON (1400°C)	EI	EI	ISO 9185
CALOR POR CONTACTO / CONTACT HEAT		FI	FI	EN ISO 12127-2
SOLDADURA / WELDING		Class 1	Class 1	EN 11611
ARCO ELÉCTRICO / ELECTRIC ARC		ATPV: 9,6 cal/cm <sup>2</sup> ELIM: 8,6 cal/cm <sup>2</sup> 4kA Class 1	No tested 4kA Class 1	EN 61482-1-1 EN 61482-1-2
ANTIESTÁTICO / ANTISTATIC		Pass	Pass	EN 1149/3/5
ANTIÁCIDO / ANTIACID (opcional/optional)*		Pass	No tested	EN 13034
ALTA VISIBILIDAD / HIGH VISIBILITY <sup>1</sup>		Pass <sup>1</sup>	Pass <sup>1</sup>	EN 20471

\*Prendas antiácidas: polimerizar 2 minutos a 160°C o aditivar con acabado fluorocarbonado tras cada ciclo de lavado.  
Antacid garments: polymerize 2 minutes at 160°C or add fluorocarbon finish after each washing cycle.

<sup>1</sup>Condiciones de lavado EN 6330 (60°C) / Washing instructions EN 6330 (60°C)


# 825 Xispal RS

Rev. 5

Sectores recomendados / Recommended use:



Petróleo y gas  
Oil & Gas



Electricidad  
Electricity



Petroquímicas  
Petrochemistry



Fundiciones (Fe/Al)  
Foundries (Fe/Al)

Normativas para prenda / Standard for garments:



Instrucciones de lavado EN 15797 (75°C) / Washing instructions EN 15797 (75°C):



Colores disponibles / Available colors:



Amarillo HV  
HV Yellow



Rojo 30  
Red 30



Gris 80  
Grey 80



Gris 82  
Grey 82



Azulina 50  
Royal Blue 50



Marino 70  
Navy Blue 70



Marino 60  
Navy Blue 60